

CAULKING SIS440

“The Professional’s Choice”



- 30 years of experience
- NO PRIMER
- 18 month shelf-life
- Stays flexible
- Cures rapidly
- Adheres permanently
- Minimum sag and shrinkage
- Highest rated resistance to UV
- Easy to work
- Black, White and Gray



SIS-440 Deck Sealant is a one-part, paste-like neutral cure caulk which, when exposed to moisture in the air, reacts to form a tough, flexible solid rubber compound. The sealant does not sag during cure, and has excellent temperature stability and chemical resistance when cured. Because the sealant is neutral cure, it is non-corrosive to all substrates.

CAT-106-Caulking SIS 440
REV: 2016-09-29

Copyright © Teakdecking Systems, Inc. All rights reserved.

Supplied by



09 4434248 | 021 220 2125
graham@tagmarine.co.nz
www.tagmarine.co.nz





PRODUCT INFORMATION SHEET

SIS-440 TEAK CAULKING

- One-Part Polymer Adhesive/Sealant - Neutral Cure
- No Primer Necessary or Recommended

SAFETY AND RELIABILITY: During cure, the sealant may irritate eyes. Care should be taken to read all caution labels and statements.

PROPERTIES		PHYSICALS	
Color	Black, White & Gray	Shore A Hardness	38-40
Specific Gravity	1.2	Tensile Strength	300 psi
Viscosity	Thixotropic Paste	Elongation	850%
Tack-Free Time	20-40 minutes	Modulus @ 100%	85 lb.
PACKAGING:			
IN CARTRIDGES	IN SAUSAGES	IN 5 GAL. (US) PAIL	
10.3 fl. oz. (305ml)	20 fl. oz. (600ml)	4.5 US gal. (17l)	

SHELF LIFE & STORAGE: Stored between 32°F - 80°F (0°C - 26°C) in the provided container, the sealant has a shelf life of eighteen months from manufacture date. Product date code on packaging is date of manufacture.

HANDLING SUGGESTIONS:

- 1.) Read and follow instructions printed on the packaging.
- 2.) Paint and varnish do not adhere well to caulking. After sanding, small particles of polymer from teak dust or other dust residue from the caulk may cause 'fisheye' in wet paint. Thoroughly vacuum off teak dust and clean surfaces with proper solvents before painting to avoid paint issues.
- 3.) Should you not completely empty the packaging in which the sealant was shipped, simply extrude approximately 1/8" beyond the tip, let cure, and you have a ready-made plug that can be pulled out easily when use is required again.
- 4.) **CLEANUP:** Use mineral spirits to clean your hands and tools from caulk. **NEVER USE MINERAL SPIRITS IN TEAK SEAMS** (acetone only).

NOTICE: The information herein is based on data available to us, and is believed reliable. Since the use of this product is beyond our control, there is no expressed or implied warranty of results, or that such use will not infringe on any patents. The product is furnished on the condition that the user will determine its suitability, and that the user assumes all legal responsibility, and that neither seller nor manufacturer shall be liable for any injury, loss, damage or consequential loss, arising from use or inability to use the product. We make no guarantee that the suggested health and safety precautions will be adequate for all individuals and/or situations.

CAT-106-Caulking SIS-440
REV: 2016-09-29

Copyright © Teakdecking Systems, Inc. All rights reserved.

Supplied by



09 4434248 | 021 220 2125
graham@tagmarine.co.nz
www.tagmarine.co.nz

